



HOUSE of KOLOR 
URETHANE KANDY

UK | KOSMIC KOLOR KANDY FACTORY PACK

Kosmic Kolor Urethane Enamel Kandys are a collection of 18 kandy colors. Due to its difficulty we suggest spraying Kandy Basecoats (KBC), for ease of application. This product is for use in US National rule areas only.

COMPONENTS

KK KANDY KONCENTRATES		
UK01 BRANDYWINE	UK07 ROOT BEER	UK13 BURPLE
UK02 LIME GOLD	UK08 TANGERINE	UK14 SPANISH GOLD
UK03 WILD CHERRY	UK09 ORGANIC GREEN	UK15 TEAL
UK04 ORIENTAL BLUE	UK10 PURPLE	UK16 MAGENTA
UK05 COBALT BLUE	UK11 APPLE RED	UK18 PINK (LIMITED USE DUE TO FADING POTENTIAL)
UK06 BURGUNDY	UK12 PAGAN GOLD	UK22 VOODOO VIOLET
CATAYLST	RU SERIES REDUCER	
KU100	RU310	RU312
KU150	RU311	RU313

PRODUCT INFORMATION

UK KOSMIC KOLOR KANDY FACTORY PACK

MIX RATIO: 2 : 1 : 1

SIZES AVAILABLE: Quart / Gallon

DRY TIME:

- Air dry at 70°F = 24 hours
- Force dry at 140°F = Allow the finish to flash 30 minutes, bake time should be 1 hour with 1 hour cool down.

Note: Apply 2-3 coats of topcoat clear allowing kandy enough time to stop "stringing". DO NOT LET KANDY TO DRY COMPLETELY or wrinkling and lifting is likely to occur.

UKK01 | URETHANE KANDY KARRIER

UKK01 Urethane Kandy Karrier is VOC compliant coast to coast. UKK01 can be applied as a medium solids Kandy or as a low solids Kandy. Simply reduce, catalyze and choose a kandy concentrate from our product line. UKK01 is the key to spraying that perfect true kandy job.

COMPONENTS

KK KANDY KONCENTRATES		URETHANE KANDY KARRIER
KK01 BRANDYWINE	KK10 PURPLE	UKK01 URETHANE KANDY KARRIER
KK02 LIME GOLD	KK11 APPLE RED	
KK03 WILD CHERRY	KK12 PAGAN GOLD	
KK04 ORIENTAL BLUE	KK13 BURPLE	
KK05 COBALT BLUE	KK14 SPANISH GOLD	
KK06 BURGUNDY	KK15 TEAL	
KK07 ROOTBEER	KK16 MAGENTA	
KK08 TANGERINE	KK18 PINK (LIMITED USE DUE TO FADING POTENTIAL)	
KK09 ORGANIC GREEN	KK22 VOODOO VIOLET	
CATAYLST	LV SERIES REDUCER	RU SERIES REDUCER
KU152 KOSMIC CATALYST	RU300	RU310
	RU301	RU311
		RU312
		RU313
		RU315

PRODUCT INFORMATION

UKK01 URETHANE KANDY KARRIER

LOW SOLIDS KANDY MIXING RATIO: 4 : 1 : 2

(Add 2-4oz KK to above sprayable QT)

MEDIUM SOLIDS KANDY MIXING RATIO: 4 : 1 : 1

(Add 2-4oz KK to above sprayable QT)

SIZES AVAILABLE: Quart / Gallon

Note: Apply 2-3 coats of topcoat clear allowing kandy enough time to stop "stringing". DO NOT LET KANDY TO DRY COMPLETELY or wrinkling and lifting is likely to occur.

DRY TIME:

- Air dry at 70°F = 24 hours
- Air dry at 70°F with AX02 added at 5% of RTS quart mix = 4-6 hours
- Force dry at 140°F = Allow the finish to flash 30 minutes, bake time should be 1 hour with 1 hour cool down.